

**MAIL STOP AMENDMENT**

Q80222

July 20, 2004

**AMENDMENTS TO THE SPECIFICATION**

Please delete the fourth full paragraph on page 9 and replace it with the following new paragraph:

In order to avoid occurrence of protrusions on the surface of the glass substrate as a result of an undissolved portion of  $\text{ZrO}_2$ , use is preferably made of a chemically strengthenable glass containing, by mol%, 57-74%  $\text{SiO}_2$ , 0-2.8%  ~~$\text{ZnO}$~~ ,  $\text{ZrO}_2$ , 3-15 wt%  $\text{Al}_2\text{O}_3$ , 7-16 wt%  $\text{Li}_2\text{O}$ , and 4-14 wt%  $\text{Na}_2\text{O}$ .